



ANR Stock

4178-E

Natural Color, EPDM-Butyl Blend

ASTM D1056 2007 2A1

25% Compression Deflection	ASTM D1056	2 – 5 lb/in ²
Oven Aged 25% Compression Deflection (7 days/70°C)	ASTM D1056	±10%
Water Absorption	ASTM D1056	<5%
Tensile Strength	ASTM D412	30 – 40 lb/in ²
Elongation	ASTM D412	120%
Density	ASTM D1056	6 – 8 lb/ft ³

10/2014