

DATA SHEET

NEOPRENE

ANR-451

Color:		Black
Specifications:	ASTM D-1056-00 ASTM D-1056-67(1) SAE J18-02 GM 6086M(3) GMN11106(3) TSM1501G	2C5 SCE45 2C5 IIIA IIIA 2C5
25% Compression Deflection (PSI)		16 - 24
Shore 00 Durometer (Approximate)		65+
Density (Approximate p.c.f.)		21 - 35
Water Absorption By Weight		5%
Temperature Range		-40 to 200F
Weather Resistance:	UV Ozone	Excellent Fair
Accelerated Linear Shrinkage (Typical)		5%
Fuel B Resistance %		150
Tensile Strength (Typical)		150 PSI
Elongation (Typical)		140%
Flammability:	FM VSS No. 302 ASTM D 6576	Pass Pass

(1)Obsolete specification listed for reference only. ANR certifies to most recent revision of ASTM D-1056 and SAE J18.

(3)Certain sections of this specification will not apply to all products. Contact Customer Service for details.

American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.